MILL TEST CERTIFICATE

Contract No.	
Customer	DUFERCO
L/C No.	
P/O No.	32201305C100
Commodity	H-BEAM
Specification	ASTM A572 G50/A992/ CSA 350W

HYUNDAI STEEL

Head Office	1, Songhyeon-dong, Dong-gu, Incheon, 401-712, S. Korea
Certificate No.	IH20130701409 - 7
Class Cert. No.	
Date of Issue	2013-07-09

Dimensions & Length	Heat No.	Pieces / Weights (kg)	Chemical Composition (%) C	Si	Mn	P	S	Cu / Ni	Mo / Cr	Al / V	Nb	Sn	CE(1)	Tensile Test: Tensile Strength	Yield point	Elongation(2)	Yield Ratio	Impact Test (V-notch): AVG (°)	1	2	3 (°C)	Remarks (Impact Specimen Size)
			×100			×1000		×100		×1000			×100	N/mm²		%						
18X11X76 40.00 FT	N 019796	2 2,758	16	14	104	21	19	26 8	2 12	4 30	21	12	39	541.3 542.3	405.0 403.1	25.0 25.5	0.75 0.74					
18X11X76 40.00 FT	N 019817	1 1,379	19	16	69	32	16	17 11	2 17	4	18	8	36	521.7 526.6	385.4 390.3	26.5 26.0	0.74 0.74					
18X11X76 40.00 FT	N 019852	3 4,137	20	16	67	25	18	20 7	2 12	4	17	10	36	539.4 540.3	402.1 404.0	25.0 25.5	0.74 0.75					
18X11X76 40.00 FT	N 019856	7 9,653	18	18	107	29	15	20 8	1 13	5	15	9	40	527.6 528.6	392.3 393.2	27.0 26.6	0.74 0.74					
18X11X76 40.00 FT	N 019861	3 4,137	19	15	69	34	15	20 7	2 10	5	15	10	36	535.4 536.4	398.1 396.2	25.5 26.0	0.74 0.74					
18X11X76 40.00 FT	N 019863	3 4,137	19	14	64	24	14	20 6	2 10	5	13	9	34	530.5 532.5	395.2 395.2	26.0 26.5	0.74 0.74					
18X11X76 40.00 FT	N 019865	6 8,274	19	14	64	26	20	24 7	2 10	4	13	10	34	556.0 551.1	418.7 414.8	24.0 24.5	0.75 0.75					
18X11X76 40.00 FT	N 019867	5 6,895	19	17	69	35	20	19 7	2 12	5	19	9	35	538.4 535.4	398.1 395.2	25.5 26.0	0.74 0.74					
18X11X76 40.00 FT	N 020094	10 13,790	18	18	67	29	17	17 7	3 14	4	14	9	34	541.3 547.2	408.5 414.6	25.5 25.0	0.76 0.76					
SUB TOTAL		48 55,160																				

(Note) (1) Ceq: (CE=C+Mn/6+Cr/5+V/5+Mo/5+Ni/15+Cu/15) (2) Gauge length : 200 mm (3) Yield Ratio = YP/TS

K. S. Shin

General Manager of Q.A Team

WE HEREBY CERTIFY THAT THE MATERIAL HAS BEEN MADE AND TESTED IN ACCORDANCE WITH THE ABOVE SPECIFICATION AND ALSO WITH THE REQUIREMENTS CALLED FOR THE ABOVE ORDER