

Chemical and Physical Test Report

MADE IN UNITED STATES

CUSTOMER: GERDAU CORSA S A PIDE CV

SHAPE + SIZE		GRAD	ÞΕ	SPEC	SPECIFICATION														SAL	SALES ORDER			CUST P.O. NUMBER			
A8 X 8 X 5/8		A572-	50T2	ASTM	A572-	50 TYP	E 2-07,	A709	GR50/3	345																
HEAT I.D.	C	Mn	P	S	Si	Cu	Ni	Cr	Мо	V	Nb	Sn	C Eqv	-				T	T T		T	_		1	1	
Y017784	.14	.99	.005	.020	.29	.19	.09	.05	.021	.027	<.008	.009	.392									-		-		

Yield 52000 PSI, 358.53 MPA Tensile: 73000 PSI, 503.32 MPA %EI: 25.0/8in, 25.0/203.2mm Corrosion Index: 4.54 Mechanical Test:

Customer Requirements CASTING: STRAND CAST

Yield 51000 PSI, 351.63 MPA Tensile: 72000 PSI, 496.42 MPA %EI: 25.0/8in, 25.0/203.2mm Corrosion Index: 4.54 Mechanical Test:

Customer Requirements CASTING: STRAND CAST

SHAPE + SIZE		GRAD	ÞΕ	SPEC	SPECIFICATION														S	SALES ORDER			CUST P.O. NUMBER			
A8 X 8 X 5/8		A572-	50T2	ASTM	A572-5	O TYP	E 2-07,	A709	GR50/3	45																
HEAT I.D.	С	Mn	Р	S	Si	Cu	Ni	Cr	Мо	V	Nb	Sn	C Eqv								T			1		
Y017788	.14	.99	.008	.022	.25	.27	.09	.07	.020	.027	<.008	.013	.394													

Mechanical Test: Yield 51000 PSI, 351.63 MPA Tensile: 72000 PSI, 496.42 MPA %EI: 26.0/8in, 26.0/203.2mm Corrosion Index: 5.35

Customer Requirements CASTING: STRAND CAST

Yield 50000 PSI, 344.74 MPA Tensile: 72000 PSI, 496.42 MPA %EI: 25.0/8in, 25.0/203.2mm Corrosion Index; 5.35 Mechanical Test:

Customer Requirements CASTING: STRAND CAST

This material, including the billets, was melted and manufactured in the United

Bhaskar Yalamanchili

Quality Director

Gerdau

THE ABOVE FIGURES ARE CERTIFIED CHEMICAL AND PHYSICAL TEST RECORDS AS CONTAINED IN THE PERMANENT RECORDS OF COMPANY.

> Metallurgical Services Manager CALVERT CITY STEEL MILL

Seller warrants that all material furnished shall comply with specifications subject to standard published manufacturing variations. NO OTHER WARRANTIES, EXPRESSED OR IMPLIED, ARE MADE BY THE SELLER, AND SPECIFICALLY EXCLUDED ARE WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

In no event shall seller be liable for indirect, consequential or punitive damages arising out of or related to the materials furnished by seller.

Any claim for damages for materials that do not conform to specifications must be made from buyer to seller immediately after delivery of same in order to allow the seller the opportunity to inspect the material in question.