CERTIFICATE NO(성적서 번호) : D202929 Page 1 of 1
DATE OF ISSUE(발행일자) : 2019-02-22
CONTRACT(P/O) NO.(계약번호) : 27795
PR NO.(주문서번호) : F181200191
COMMODITY(제품명) : E.R.W. CARBON STEEL PIPE
SPECIFICATION(제품규격) : ASTM A53 B

검사증명서
MILL TEST CERTIFICATE
EN 10204 TYPE 3.1 - 2004

CUSTOMER(고객사): PLESA ANAHUAC Y CIAS., S.A. DE C.V.

HYUNDAI STEEL

출산공장 : 울산광역시 북구 염포로 706
706, Yeompo-ro, Buk-gu, Ulsan, Korea

No.	TYPE OF PIPE END ※1	SIZE OUT-DIA×THICK×LENGTH (외경×두께×길이)	PCS (본)	WEIGHT (KG)	TOTAL LENGTH (M)	HEAT No.	Hydrostatic Test Pressure (PSI)	Hydrostatic Test Time (SEC)	Spec.	※2	Tensile Properties(Gage Length : 2 inch) Tensile Strength Base (MPa)	Tensile Strength Weld (MPa)	Yield Strength (MPa)	Y/R Rate (%)	E.L (%)	Hardness Test ※3	Hardness Test & CVN Impact Test ※2 ※3	CVN Impact Test(℃) Specimen size	CVN Impact Test(℃) Absorbed Energy(Joule) 1	2	3	avg	Shear Area (%)	D.W.T Test(℃) Shear Area(%) 1	2	avg
									Min.		415	415	240		28											
									Max.									Criteria : In the case of 10×10								
1	EB BE	20" X 0.375 " X 6.150 M	62	44,620	381.3	P85706	788	5		T	476	490	351		39											
		TOTAL	62	44,620	381.3																					

No.	Heat No.	Spec.	※4	Chemical Composition(%) C	Si	Mn ※7	P	S	Cu	Ni	Cr	Mo	V	CM3 ※10	2 :×100 3 :×1000 4 :×10000	Zn-Coating Test Zn Coating	Copper Sulfate Test Time	Copper Sulfate Test Result	HC-Test Collapse Pressure	H.I.C Test CLR	CTR	CSR	S.S.C.C Test
		Min.		2	2	2	3	3	2	2	2	3	3	3					psi	%	%	%	
		Max.		30		120	50	45	40	40	40	150	80	1000									
	P85706		H	6	2	78	11	4															
			P	6	1	78	13	7	1	1	2	1	1	37									
			P	7	2	79	14	8	1	1	2	1	1	39									

Remark
※1) Type of pipe end(관종)
EB:E-W Black BE:Bevel End
※2) L: Longitudinal, T: Transverse
※3) B: Base, W: Weld Line, H: Heat Affected Zone
※4) H: Heat(Ladle) Analysis, P: Product Analysis
※7) For each reduction of 0.01% below the specified C max.
an increase of 0.06% Mn above the specified max.
will be permitted up to a max of 1.65%
※10) CM3=Cu+Ni+Cr+Mo+V
※ SPEC YEAR – ASTM A53(2018ED)

Heat Treatment	Non-Destructive Test (U.T)	Flattening / Bending Test	Visual & Dimension
GOOD	GOOD	GOOD	GOOD

SURVEYOR

본 제품은 관련 규격에 합격되었음을 보증합니다.
WE HEREBY CERTIFY THAT MATERIAL DESCRIBED HEREIN HAS BEEN ACCEPTED IN ACCORDANCE WITH THE PRESCRIBED SPECIFICATION AND ORDER.
* 본 검사증명서에 명기된 규격용도외 사용시 안전상 문제가 발생할 수 있으며, 검사증명서 위,변조시 사문서 위조로 불이익을 당하실 수 있습니다.

H.K. CHOI
QA Manager

* 본 검사증명서는 원본인 전자문서(전자서명 정보 포함)로부터 출력된 사본입니다. 전자문서의 내용은 현대제철 고객포탈에서 확인하실 수 있습니다.(http://sm.hyundai-steel.com/cs/cm/login.jsp)
* This Mill Test Certificate is a copy that has been printed from original electronic document(with digital signing).
You are able to check an original electronic document at hyundaisteel's customer portal.(http://sm.hyundai-steel.com/cs/cm/login.jsp) * QRcode scanner App : 'QReal'