

# 검사증명서

## MILL TEST CERTIFICATE



당진제철소 : 충남 당진시 송악읍 북부산업로 1480  
1480 Bukbusanup-Ro, Songak-Eup, Dangjin-Si, Chungnam, Korea

주문번호 : F191100036  
Order No.

품명 : HOT ROLLED STEEL PLATE  
Commodity

제품규격 : ASTM A36  
Specification

고객사 : PLESA STEEL  
Customer

주문자 : HYUNDAI CORPORATION  
Contractor

증명서 번호 : 20191224-PS-004-066  
Certificate No.

발행일자 : 2019-12-24  
Date of Issue

제품치수 Dimension	수량 Quantity	중량 Weight (Kg)	제강번호 Heat No.	제품번호 Product No.	Position	인장시험 Tensile Test						화학성분 Chemical Composition(%)															
						YP	TS	EL	YP-EL	RA	YR	YP Mtd	Division	단위 Unit 2 : x100 3 : x1,000 4 : x10,000 5 : x100,000													
						(N/mm <sup>2</sup> )	(%)	(%)	(%)	(%)		C		Si	Mn	P	S	Cr	Ni	Cu	Mo	Nb	Ti	V	Sol-Al	DR	
38.1 x 1829 x 6096	1	3,335	R32574	FC15455902	T	296.6	476.7	30				U	L	1,559	248	1,021	149	40	2	1	17	0	1	2	0	30	1,956
38.1 x 1829 x 6096	1	3,335	R32574	FC15455904	T	296.6	476.7	30				U	P	1,670	244	1,033	137	36	2	1	18	0	1	2	1	29	1,956
38.1 x 1829 x 6096	1	3,335	R32574	FC15456101	T	289.0	472.2	31				U	P	1,670	244	1,033	137	36	2	1	18	0	1	2	1	29	1,956
38.1 x 1829 x 6096	1	3,335	R32574	FC15456104	T	289.0	472.2	31				U	L	1,559	248	1,021	149	40	2	1	17	0	1	2	0	30	1,956
													P	1,670	244	1,033	137	36	2	1	18	0	1	2	1	29	1,956

\*\*\* Sub Total(020) \*\*\* 12 40,020(Kg)

\*\*\* Condition of supply : As-Rolled \*\*\*

NOTE  
\* Position - T:Top, M:Middle, B:Bottom  
\* Tensile test - Direction:Transverse, Gauge length:200mm (Rectangular), YP Mtd : 2 (0.2% off-set), 5 (0.5% underload), U (Upper yield point), L (Lower yield point)  
\* Division - P:Product analysis, L:Ladle analysis

\* The plate is fully killed and fine grained steel. Basic oxygen process and Vacuum degassing process were applied.\* This Mill Test Certificate is issued in accordance with EN 10204 Type 3.1

상기의 제품은 검사의 결과 지정된 규격에 합격한 것을 증명합니다.  
WE HEREBY CERTIFY THAT THE MATERIAL HAS BEEN MADE AND TESTED IN ACCORDANCE WITH THE ABOVE SPECIFICATION AND THE REQUIREMENTS

Signature

S. B. Park

Chief Of Quality Assurance Team