

FACTORY:



GLOBEFIT MANUFACTURING SDN BHD
JALAN PSS 2 TAMA PERINDUSTRIAN SUNGAL SEDU
SANGAI SEDU 42700 BANTING MALAYSIA

TEL : 03 90596888

E-MAIL:GLOBEFIT@ggfit.my

CONTACT NAME: JASON

SELLER:

GLOBEFIT MANUFACTURING SDN BHD
JALAN PSS 2 TAMA PERINDUSTRIAN SUNGAL SEDU
SANGAI SEDU 42700 BANTING MALAYSIA

S.C. NUMBER:

511-37-61

PAGE

1/1

DATE:

JUL.17-2019

L.C. N°:

CIA / TT

DELIVERY:

CIF MANZANILLO, MEX.

ORIGINAL FACTORY CERTIFICATE

EN 10204B 3.1

COUNTRY OF ORIGIN:

MALAYSIA

EXPORTER COUNTRY:

MALAYSIA

NO.	A-234 WPB ASME B16.9			HEAT NO.	CHEMICAL COMPOSITION (A234)										PHYSICAL PROPERTIES				SURFACE
	DESCRIPTION	QTY			C	Si	Mn	P	S	Ni	Cr	Mo	Cu	V	T.S	Y.S	EL%	HB	
					≤0.30	≥0.10	0.29-1.06	≤0.05	≤0.058	≤0.40	≤0.40	≤0.15	≤0.40	≤0.08	415-655	≥240	≥22	≤197	
23	EL 90° LR A-234 WPB XH ASME B16.9	6	120	843	0.21	0.2	0.51	0.0025	0.0015	0.014	0.012	0.005	0.003	0.006	500	312	34	165	GOOD
24	EL 90° LR A-234 WPB XH ASME B16.9	8	50	843	0.21	0.2	0.51	0.0025	0.0015	0.014	0.012	0.005	0.003	0.006	500	312	34	165	GOOD
25	EL 90° LR A-234 WPB XH ASME B16.9	12	5	529	0.2	0.25	0.5	0.0025	0.003	0.011	0.01	0.015	0.04	0.022	460	320	32	160	GOOD
26	EL 90° LR A-234 WPB S/160 ASME B16.9	1	20	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
27	EL 90° LR A-234 WPB S/160 ASME B16.9	1/2"	20	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
28	EL 90° LR A-234 WPB S/160 ASME B16.9	3/4"	20	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
29	EL 90° LR A-234 WPB S/160 ASME B16.9	1 1/2"	30	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
30	EL 90° LR A-234 WPB S/160 ASME B16.9	1 1/4"	10	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
31	EL 90° LR A-234 WPB S/160 ASME B16.9	2	20	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
32	EL 90° LR A-234 WPB S/160 ASME B16.9	2 1/2"	20	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
33	EL 90° LR A-234 WPB S/160 ASME B16.9	3	20	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
34	EL 90° LR A-234 WPB S/160 ASME B16.9	4	50	843	0.21	0.2	0.51	0.0025	0.0015	0.014	0.012	0.005	0.003	0.006	500	312	34	165	GOOD
35	EL 90° LR A-234 WPB S/160 ASME B16.9	6	30	843	0.21	0.2	0.51	0.0025	0.0015	0.014	0.012	0.005	0.003	0.006	500	312	34	165	GOOD
36	EL 90° LR A-234 WPB S/160 ASME B16.9	8	10	843	0.21	0.2	0.51	0.0025	0.0015	0.014	0.012	0.005	0.003	0.006	500	312	34	165	GOOD
37	EL 45° LR A-234 WPB STD ASME B16.9	3/4"	200	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
38	EL 45° LR A-234 WPB STD ASME B16.9	1 1/2"	2000	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
39	EL 45° LR A-234 WPB STD ASME B16.9	1 1/4"	500	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
40	EL 45° LR A-234 WPB STD ASME B16.9	1	500	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
41	EL 45° LR A-234 WPB STD ASME B16.9	2	300	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
42	EL 45° LR A-234 WPB STD ASME B16.9	2 1/2"	200	956	0.19	0.23	0.52	0.0025	0.002	0.014	0.011	0.002	0.003	0.01	498	320	33	160	GOOD
43	EL 45° LR A-234 WPB STD ASME B16.9	4	400	843	0.21	0.2	0.51	0.0025	0.0015	0.014	0.012	0.005	0.003	0.006	500	312	34	165	GOOD
44	EL 45° LR A-234 WPB STD ASME B16.9	6	79	843	0.21	0.2	0.51	0.0025	0.0015	0.014	0.012	0.005	0.003	0.006	500	312	34	165	GOOD

We hereby certify that above mentioned products are in accordance with the requirements of the order and specifications and have been checked without objection for surface and dimensionnel control.

Carbon steel fittings A-234 WPB / ASME B16.9

HEAT TREATMENT NORMALIZED AT 910 C AND COOLED IN STILL AIR NACE MR 0103 2010

Quality dept.

