



Standard Specification for Steel, Sheet and Strip, Heavy-Thickness Coils, Hot-Rolled, Carbon, Commercial, Drawing, Structural, High-Strength Low-Alloy, and High-Strength Low-Alloy with Improved Formability¹

This standard is issued under the fixed designation A 1018/A 1018M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope*

1.1 This specification covers hot-rolled, heavy-thickness coils beyond the size limits of Specification A 1011/A 1011M.

1.2 The product is available in five designations: Commercial Steel, Drawing Steel, Structural Steel, High-Strength Low-Alloy Steel, and High-Strength Low-Alloy Steel with Improved Formability.

1.3 This material is available only in coils described as follows:

Product	Size Limits, Coils Only	
	Width, in. [mm]	Thickness, in. [mm]
Strip	Over 8 to 12, incl [Over 200 to 300]	0.230 to 1.000, incl [Over 6.0 to 25]
Sheet	Over 12 to 48, incl [Over 300 to 1200]	0.230 to 1.000, incl [Over 6.0 to 25]
Sheet	Over 48 [Over 1200]	0.180 to 1.000, incl [Over 4.5 to 25]

1.4 Sheet and strip in coils of sizes noted in 1.3 are covered by this specification only with the following provisions:

1.4.1 The material is to be fed directly from coils into a blanking press, drawing or forming operation, tube mill, rolling mill, or sheared or slit into blanks for subsequent drawing or forming.

1.4.2 The material is not to be converted into steel plates for structural or pressure vessel use unless tested in complete accordance with the appropriate sections of Specifications A 6/A 6M (plates provided from coils) or A 20/A 20M (plates produced from coils). Plate produced in this manner is no longer governed by this sheet steel specification and since this material is now plate, the appropriate plate standard shall apply.

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.19 on Steel Sheet and Strip.

Current edition approved April 1, 2004. Published April 2004. Originally approved in 2001. Last previous edition approved in 2003 as A 1018/A 1018M – 03a.

1.4.3 The dimensional tolerances of Specification A 635/A 635M are applicable to material produced to this specification.

1.4.4 Not all strength levels are available in all thicknesses. The user should consult the producer for appropriate size limitations.

1.5 The values stated in either inch-pound units or SI units [metric] are to be regarded separately as standard. Within the text the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other.

2. Referenced Documents

2.1 ASTM Standards:²

A 6/A 6M Specification for General Requirements for Rolled Structural Steel Bars, Plates, Shapes, and Sheet Piling

A 20/A 20M Specification for General Requirements for Steel Plates for Pressure Vessels

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products

A 635/A 635M Specification for Steel, Sheet and Strip, Heavy-Thickness Coils, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy, and High-Strength Low-Alloy with Improved Formability, General Requirements for A 751 Test Methods, Practices, and Terminology for Chemical Analysis of Steel Products

A 1011/A 1011M Specification for Steel, Sheet and Strip, Hot-Rolled, Carbon, Structural, High-Strength Low-Alloy and High-Strength Low-Alloy with Improved Formability
E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications
G 101 Guide for Estimating the Atmospheric Corrosion

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

*A Summary of Changes section appears at the end of this standard.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

Resistance of Low-Alloy Steels

3. General Requirements for Delivery

3.1 Material furnished under this specification shall conform to the applicable requirements of the current edition of Specification A 635/A 635M, unless otherwise provided herein.

4. Classification

4.1 Heavy thickness coils are available in the following designations:

4.1.1 *Commercial Steel (CS)*

4.1.2 *Drawing Steel (DS)*

4.1.3 *Structural Steel*—(SS grades 30[205], 33[230], 36[250] Types 1 and 2, and 40[275]).

4.1.4 *High-Strength Low-Alloy Steel*—(HSLAS grades 45[310], 50[340], 55[380], 60[410], 65[450], 70[480]) in Classes 1 and 2.

4.1.4.1 This material is intended for miscellaneous applications where greater strength and savings in weight are important. The material is available in two classes. They are similar in strength level, except that Class 2 offers improved weldability and more formability than Class 1. Atmospheric corrosion resistance of these steels is equivalent to plain carbon steels. With copper specified, the atmospheric corrosion is somewhat enhanced.

4.1.5 *High-Strength Low-Alloy Steel with Improved Formability*—(HSLAS-F grades 50[340], 60[410], 70[480], 80[550]).

4.1.5.1 This material has improved formability when compared with HSLAS. The steel is killed and made to a fine ferritic grain practice and includes microalloying elements such as columbium, titanium, vanadium, zirconium, etc. The steel shall be treated to achieve inclusion control. The material is intended for miscellaneous applications where higher strength, savings in weight, improved formability, and weldability are important. Atmospheric corrosion resistance of these steels is equivalent to plain carbon steels. With copper specified, the atmospheric corrosion resistance is somewhat enhanced.

NOTE 1—For methods of establishing the atmospheric corrosion resistance of low-alloy steels, see Guide G 101.

4.1.6 When required for HSLAS and HSLAS-F steels, limitations on the use of one or more of the microalloy elements shall be specified on the order.

5. Ordering Information

5.1 Orders for material under this specification shall include the following information, as required, to describe adequately the desired material.

5.1.1 ASTM specification number and year of issue.

5.1.2 Name of material and designation (hot-rolled steel sheet or hot-rolled strip) (include grade and, as appropriate, type and class for CS, DS, SS, HSLAS, and HSLAS-F) (see section 4.1).

5.1.2.1 For HSLAS, when a class is not specified class 1 will be furnished) (see section 4.1),

5.1.3 Copper bearing, (if required),

5.1.4 *Condition*—Material in accordance with this specification is furnished in the hot rolled condition. Pickled (or blast cleaned) must be specified if required. Material ordered as pickled (or blast cleaned) will be oiled unless ordered dry,

5.1.5 Type of edge must be specified for hot rolled sheet coils and strip coils, either mill edge or cut edge (sheet), mill edge or slit edge (strip),

5.1.6 Dimensions (decimal thickness and width of material),

5.1.6.1 As agreed upon between the purchaser and the producer, material ordered to this specification will be supplied to meet the appropriate standard or restricted thickness tolerances shown in Specification A 635/A 635M,

NOTE 2—Not all producers are capable of meeting all the limitations of the thickness tolerance tables in Specification A 635/A 635M. The purchaser should contact the producer regarding possible limitations prior to placing an order.

5.1.7 Coils size and weight requirements (must include inside diameter (ID), outside diameter (OD), and maximum weight,

5.1.8 Quantity (weight),

5.1.9 Application (part identification and description).

5.1.10 Special requirements, if required, and

5.1.11 A report is required of heat analysis and mechanical properties as determined by the tension test.

NOTE 3—A typical ordering description is as follows: (inch pound units) ASTM A 1018/A 1018M: Grade 50, High-Strength, Low-Alloy, Class 2, hot rolled sheet coils, pickled and oiled, cut edge, 0.500 by 40 in. by coil; ID 24 in., OD 72 in., maximum; coil weight 40 000 lb., maximum; 200 000 lb. for roll forming shapes; (SI units) ASTM A 1018/A 1018M: Grade 345, High-Strength Low-Alloy, Class 2, hot-rolled sheet coils, pickled and oiled, cut edge; 10 mm by 900 mm by coil; ID 600 mm, OD 1800 mm, maximum; coil weight 18 000 kg maximum; 90 000 kg for roll forming shapes.

6. Chemical Composition

6.1 The heat analysis of commercial steel and drawing steel shall conform to the requirements of Table 1.

6.1.1 The heat analysis of structural steel, high-strength low-alloy steel, and high-strength low-alloy steel with improved formability shall conform to the requirements of Table 2.

6.1.2 Chemical analysis shall be conducted in accordance with Test Method A 751.

6.1.3 Each of the elements listed in Tables 1 and 2 shall be included in the report of the heat analysis. When the amount of copper, nickel, chromium, or molybdenum is less than 0.02 %, report the analysis as <0.02 % or the actual value. When the amount of columbium, titanium, or vanadium is less than 0.008 %, report the analysis as <0.008 % or the actual determined value.

6.1.4 For Structural Steel (SS) the addition of microalloying elements, including columbium, vanadium, or titanium, as well as nitrogen, as strength enhancers is prohibited.

6.1.5 Sheet steel grades defined by this specification are suitable for welding if appropriate welding conditions are selected. For certain welding processes, more restrictive composition limits may be desirable and should be requested at the time of inquiry and ordering.

TABLE 1 Chemical Requirements
Commercial and Drawing Steels

% Heat Analysis, Element Maximum Unless Otherwise Indicated Composition Limits											
Designation Commercial Steel (CS)	C	Mn	P	S	Cu ^A	Ni	Cr	Mo	V	Cb	Ti
1006	0.08	0.45	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1008	0.10	0.50	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1009	0.15	0.60	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1010	0.08 to 0.13	0.30 to 0.60	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1012	0.10 to 0.15	0.30 to 0.60	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1015	0.12 to 0.018	0.30 to 0.60	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1016	0.12 to 0.018	0.60 to 0.90	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1017	0.14 to 0.20	0.30 to 0.60	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1018	0.14 to 0.20	0.60 to 0.90	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1019	0.14 to 0.20	0.70 to 1.00	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1020	0.17 to 0.23	0.30 to 0.60	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1021	0.17 to 0.23	0.60 to 0.90	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1022	0.17 to 0.23	0.70 to 1.00	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1023	0.19 to 0.25	0.30 to 0.60	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
1524	0.18 to 0.25	1.30 to 1.65	0.030	0.035	0.20	0.20	0.15	0.06	0.008	0.008	0.008
Drawing Steel (DS)	0.10	0.50	0.030	0.020	0.20	0.20	0.15	0.06	0.008	0.008	0.008

^A When copper is specified, the limit is a minimum requirement. When copper is not specified, the limit is a maximum.

TABLE 2 Chemical Composition^A For Hot Rolled, Heavy Thickness Coils

Designations SS, HSLAS, and HSLAS-F % Heat Analysis, Element Maximum unless otherwise shown												
Designation	C	Mn	P	S	Cu ^B	Ni	Cr	Mo	V	Cb	Ti	N
SS												
Grade 30 [205]	0.25	1.50	0.035	0.04	0.20	0.20	0.15	0.06	0.008	0.008	0.008	0.014
Grade 33 [230]	0.25	1.50	0.035	0.04	0.20	0.20	0.15	0.06	0.008	0.008	0.008	0.014
Grade 36 [250] Type 1	0.25	1.50	0.035	0.04	0.20	0.20	0.15	0.06	0.008	0.008	0.008	0.014
Grade 36 [250] Type 2	0.25	1.50 ^C	0.035	0.04	0.20	0.20	0.15	0.06	0.008	0.008	0.008	0.014
Grade 40 [275]	0.25	1.50	0.035	0.04	0.20	0.20	0.15	0.06	0.008	0.008	0.008	0.014
HSLAS ^D												
Grade 45 [310] Class 1	0.22	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	...
Grade 45 [310] Class 2	0.15	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	E
Grade 50 [340] Class 1	0.23	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	...
Grade 50 [340] Class 2	0.15	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	E
Grade 55 [380] Class 1	0.25	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	...
Grade 55 [380] Class 2	0.15	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	E
Grade 60 [410] Class 1	0.26	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	...
Grade 60 [410] Class 2	0.15	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	E
Grade 65 [450] Class 1	0.26	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	...
Grade 65 [450] Class 2	0.15	1.50	0.04	0.04	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	E
Grade 70 [480] Class 1	0.26	1.65	0.04	0.04	0.20	0.20	0.15	0.16	0.005 min	0.005 min	0.005 min	...
Grade 70 [480] Class 2	0.15	1.65	0.04	0.04	0.20	0.20	0.15	0.16	0.005 min	0.005 min	0.005 min	E
HSLAS-F ^D												
Grade 50 [340]	0.15	1.65	0.025	0.035	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	E
Grade 60 [410]	0.15	1.65	0.025	0.035	0.20	0.20	0.15	0.06	0.005 min	0.005 min	0.005 min	E
Grade 70 [480]	0.15	1.65	0.025	0.035	0.20	0.20	0.15	0.16	0.005 min	0.005 min	0.005 min	E
Grade 80 [550]	0.15	1.65	0.025	0.035	0.20	0.20	0.15	0.16	0.005 min	0.005 min	0.005 min	E

^A An ellipsis (...) indicates that no limits have been set for that element.

^B When copper steel is specified, the limit for copper is a minimum requirement. When copper is not specified the copper limit is a maximum.

^C For product greater than 0.75 in. in thickness, the manganese requirement is 0.80 to 1.20 %.

^D HSLAS and HSLAS-F steels contain the strengthening elements columbium, vanadium, and titanium added singly or in combination. The minimum requirements only apply to the microalloy elements selected for strengthening of the steel.

^E The purchaser has the option of restricting the nitrogen content. It should be noted that, depending on the microalloying scheme (for example, use of vanadium) of the producer, nitrogen may be a deliberate addition. Consideration should be made for the use of nitrogen binding elements (for example, vanadium, titanium).

7. Mechanical Properties

7.1 Test specimen preparation and mechanical testing shall be in accordance with Test Methods A 370.

7.2 *Tensile Properties*—The material, structural steel, high-strength low-alloy steel, and high-strength low-alloy steel with improved formability, as represented by the test specimens shall conform to the mechanical property requirements as

stated in Table 3. These requirements do not apply to the uncropped ends of unprocessed coils.

7.3 *Tension Test Specimen Location and Orientation*—Tension test specimens shall be taken sufficiently far from the as hot-rolled coil ends so that the sample is representative of material which received the designed processing. The test shall be taken approximately midway between the center and edge

TABLE 3 Mechanical Property Requirements^A For Hot Rolled Heavy Thickness Coils

Designations SS, HSLAS, and HSLAS-F				
Designation	Yield Strength min	Tensile Strength min ^B	Elongation in 2 in. [50 mm], min, % for thicknesses to 1 in. [25 mm] incl	
			Elongation in 8 in. [200 mm], min, % for thicknesses 0.180 in. [4.5 mm] to 1 in. [25 mm] incl	
SS				
Grade 30 [205]	30 [205]	49 [340]	22	17
Grade 33 [230]	33 [230]	52 [360]	22	16
Grade 36 [250] Type 1	36 [250]	53 [365]	21	15
Grade 36 [250] Type 2	36 [250]	58 to 80 [400 to 550]	21	18
Grade 40 [275]	40 [275]	55 [380]	19	14
HSLAS				
Grade 45 [310] Class 1	45 [310]	60 [410]	22	17
Grade 45 [310] Class 2	45 [310]	55 [380]	22	17
Grade 50 [340] Class 1	50 [340]	65 [450]	20	16
Grade 50 [340] Class 2	50 [340]	60 [410]	20	16
Grade 55 [380] Class 1	55 [380]	70 [480]	18	15
Grade 55 [380] Class 2	55 [380]	65 [450]	18	15
Grade 60 [410] Class 1	60 [410]	75 [520]	16	14
Grade 60 [410] Class 2	60 [410]	70 [480]	16	14
Grade 65 [450] Class 1	65 [450]	80 [550]	14	12
Grade 65 [450] Class 2	65 [450]	75 [520]	14	12
Grade 70 [480] Class 1	70 [480]	85 [590]	12	10
Grade 70 [480] Class 2	70 [480]	80 [550]	12	10
HSLAS-F				
Grade 50 [340]	50 [340]	60 [410]	22	16
Grade 60 [410]	60 [410]	70 [480]	16	14
Grade 70 [480]	70 [480]	80 [550]	12	10
Grade 80 [550]	80 [550]	90 [620]	12	10

^A For coil products, testing by the producer is limited to the end of the coil. Mechanical properties throughout the coil shall comply with the minimum values specified.

^B A minimum and maximum tensile strength are specified for SS Grade 36 Type 2.

of the material as rolled. For coils wider than 24 in. [600 mm], Tension test specimens shall be taken such that the longitudinal axis of the specimens is perpendicular to the direction of rolling (transverse test). For coils through 24 in. [600 mm] in width, tension test specimens shall be taken such that longitudinal axis of the specimen is parallel to the direction of rolling (longitudinal test).

7.4 Tension Tests—Two tension tests shall be conducted from each heat or each of 50 tons [45 Mg]. When the amount of finished material from a heat is less than 50 tons [45 Mg], only one tension test shall be conducted. When material rolled from one heat differs 0.050 in. [1.3 mm] or more in thickness, one tension test shall be conducted from both the thickest and the thinnest material rolled regardless of the weight represented.

7.5 To determine conformance with this specification, a test value should be rounded to the nearest 1 ksi [7 Mpa] of tensile strength and yield point, and to the nearest unit in the right-hand place of figures used in expressing the limiting value for other places in accordance with the rounding off methods given in Practice E 29.

7.6 Structural steel, high-strength low-alloy steel, and high-strength low-alloy steel with improved formability covered by this specification are commonly fabricated by cold bending. There are many interrelated factors that affect the ability of a given steel to cold form over a given radius under shop conditions. These factors include thickness, strength level, degree of restraint, relationship to rolling direction, chemistry, and microstructure. The producer shall be consulted concerning the recommended minimum inside radius and bending

direction. Where possible, a larger radius or “easy way” bending (with the bend axis perpendicular to rolling direction), or both, are recommended for improved performance.

7.7 Fabricators must be aware that cracks may initiate upon bending a sheared or burned edge. This is not considered a fault of the steel, but is rather a function of the induced cold work or heat affected zone.

8. Workmanship, Finish, and Appearance

8.1 Edges—The normal edge condition in heavy-thickness coils is mill edge. If cut edge is required, it must be specified.

8.2 Oiling—Unless otherwise specified, hot-rolled as-rolled material shall be furnished dry, and hot rolled pickled or blast cleaned material shall be furnished oiled. When required, it is permissible to specify pickled or blast cleaned material be furnished dry, or that as-rolled material be furnished oiled.

8.3 Surface Finish—Unless otherwise specified, hot-rolled material shall have an as-rolled, not pickled surface finish. When required, material shall be specified to be pickled or blast-cleaned.

9. Retests

9.1 If the results on an original tensile specimen are within 2000 psi [14 Mpa] of the required tensile strength, within 1000 psi [7 Mpa] of the required yield strength, or within 2 percentage points of the required elongation, a retest shall be permitted and a test specimen, selected at random, shall be tested. If the results on this retest specimen satisfy the specified mechanical requirements, the material shall be accepted.

10. Certification

10.1 A report of heat analysis shall be supplied, if requested, for CS and DS steels. For material with required mechanical properties, SS, HSLAS, and HSLAS-F, a report is required of heat analysis and mechanical properties as determined by the tension test.

11. Keywords

11.1 alloy steel sheet; alloy steel strip; carbon; carbon steel sheet; carbon steel strip; heavy-thickness coils; high-strength low-alloy steel; hot-rolled steel sheet; hot-rolled steel strip; improved formability; steel sheet; steel strip; structural applications

APPENDIX

(Nonmandatory Information)

X1. BENDING PROPERTIES—STRUCTURAL STEEL, HIGH-STRENGTH LOW-ALLOY STEEL, AND HIGH-STRENGTH LOW-ALLOY STEEL WITH IMPROVED FORMABILITY

TABLE X1.1 Suggested Minimum Inside Radius for Cold Bending

NOTE 1—(*t*) equals a radius equivalent to the steel thickness

NOTE 2—The suggested radius should be used as a minimum for 90° bend in actual shop practice.

NOTE 3—Material that does not perform satisfactorily, when fabricated in accordance with the above requirements, may be subject to rejection pending negotiation with the steel supplier.

Product	Grade	Minimum Inside Radius for Cold Bending	
		Class 1	Class 2
Structural Steel	30 [205]	1t	
	33 [230]	1t	
	36 [250] Type 1	1½t	
	36 [250] Type 2	2t	
	40 [275]	2t	
	45 [310]	2t	
	50 [340]	2½t	
	55 [380]	3t	
High-Strength Low-Alloy Steel	45 [310]	1½t	1½t
	50 [340]	2t	1½t
	55 [380]	2t	2t
	60 [410]	2½t	2t
	65 [450]	3t	2½t
	70 [480]	3½t	3t
High-Strength Low-Alloy Steel with Improved Formability	50 [340]	1t	
	60 [410]	1½t	
	70 [480]	2t	
	80 [550]	2t	

SUMMARY OF CHANGES

This section contains the principal changes to the standard that have been incorporated since the last issue, A 1018/A 1018M – 03a, that may impact the use of this standard. (Approved April 1, 2004.)

- | | |
|---|--|
| <ul style="list-style-type: none"> (1) New title. (2) Added reference to CS and DS steels to 1.2. (3) Deleted old Section 1.4.2. (4) Reordered Sections 1.4.1 and 1.4.3. (5) Revised title of A 635/A 635M in Section 2. (6) Added reference to CS and DS steels in Section 4. (7) Added designation CS And DS steels in 5.1.2. (8) Added reference to CS and DS steels and new Table 1 to 6.1. (9) Added reference to SS, HSLAS, and HSLAS-F and renumbered table to 6.1.2. | <ul style="list-style-type: none"> (10) Added reference to SS, HSLAS, and HSLAS-F to 7.2 and renumbered Table 3. (11) Added reference to SS, HSLAS, and HSLAS-F to 7.6. (12) Revised 10.1 to reflect addition of CS and DS to standard. (13) Added new Table 1 from A 635/A 635M. (14) Type 1 added to existing SS Grade 36. (15) Expanded Appendix X1 to include SS and HSLAS steels. (16) SS Grade 36 Type 2 added. (17) The following changes were made to Table 2: |
|---|--|



A 1018/A 1018M – 04

- (18) Revised minimum limit for columbium from 0.01 % to 0.005 %.
- (19) Footnotes B and D added.
- (20) Added items for titanium.
- (21) Revised limits for vanadium.
- (22) Delete old Footnotes B and D.
- (23) Added reference to Ti to new Footnote C.
- (24) Added information to new Footnote C, indicating the minimum limits apply only to the specific elements used to strengthen the steel.
- (25) Deleted old Footnote F.

This section contains the principal changes to the standard that have been incorporated since the last issue, A 1018/A 1018M – 03, that may impact the use of this standard. (Approved Oct. 1, 2003.)

- (1) Added Section 4.1.4.
- (2) Revised Section 5.1.10.
- (3) Deleted Supplementary Requirement S1.
- (4) Revised Tables 1 and 2.

This section contains the principal changes to the standard that have been incorporated since the last issue, A 1018/A 1018M – 02, that may impact the use of this standard. (Approved April 10, 2003.)

- (1) The following sections were revised: 4.1.3.1, 6.1.2, 7.6, 7.7, 8.1, 8.2, and 8.3.
- (2) Table 2 was revised.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).