

P.O.Box 279

(252) 356-3700 Winton, NC 27986

## Mill Test Report

It's our Nature."

Specification: Vehicle No: Issuing Date: 09/26/2005 **ALY 91723** B/L Nov. 109438

1.0000 × 96.000 x 240.000" / 25mm x 2438mm x 6096mm

ASTM A36-05/ASTM A709 Grade 36-05/ASME SA36-03a

Load No.: 111495

Our Order No.: 37805/3

Sold To: Duferco Steel Inc MATAWAN, NJ 07747 Suite 400 100 Matawan Road

> Cust. Order No.: 1003010027

Ship To: DUFERCO STEEL C/O PLESA ANAHUAC

FOR FURTHERANCE INTO MEXICO

**LECHERIA, MEX 54940** SPECIALIST IN TRANSIT FORWARDING LAREDO TX

Marking:

					_		_			
5106284-04	Metric Results Plate Serial No	5106285-02	5106285-01	5106284-04	No No	Distance	5106285	5106284	Heat No	
1	Pieces	4	13	1	Pieces		0.18	0.19	C	
	Ter Dir.				Dir.	Tei	0.88	0.88	Mo	
308 304	Tensile Test (MPa) ir. Yield	44,400 45,600	44,400 45,600	44,600 44,100	(psi) Yield	Tensile Test	0.014		P	
497 497	(MPa) Tensile	73,000 74,300	73,000 74,300	72,100 72,100	(psi) Tensile		0.001		S	
	Elongation % in 2"				Elongation Elongation % in 2" % in 8"		0.18 (		Si	
		s ; ~			on Elo		0.26	0.24	Cu	
23.2 21.8	Elongation % in 8"	21.0 22.3	21.0 22.3	23.2 21.8	% in 8"		0.08	0.08	Z.	
94. gg	Dir.				Dir.		0.11	0.10	Cr	
	_				_		0.01	0.01	Mo	
	(%) shear				(%) shear		0.010	0.009	Alz	
	N				2		0.004	0.004	<	
	C (%) shear	=			(%) shear	C	0.001	0.001	Nb	
	Charpy Impacts (%) shea				ω	Charpy Impacts	0.001	0.001	=!	
	npacts (%) shear				(%) shear	npacts	0.001 0.001 0.0089 0.0010 0.0003	0.0100	z	
	Ave.				Ave.		0.0010	0.0013	Ca	
	(%) shear				(%) shear		0.0003	0.0003	В	
	Size				Size		0.005	0.003	Sn	
	Temp				Temp		0.37	0.38	CEQ	
	Min Ave.				Min Temp Ave.		0.25	0.26	PCM	

Mercury has not been used in the direct manufacturing of this material. Produced as continuous cast as-rolled discrete plate Yield by 0.5EUL method unless otherwise specified. Ceq = C+(Mn/6)+((Cr+Mo+V)/5)+((Cu+Ni)/15)Manufactured to fully killed practice by Electric Arc Furnace. Welding or weld repair was not performed on this material

Melted and manufactured in the USA. ISO 9001-2000 certified (#12443-0) by SRI Quality System Registrar (#0985-09), PED 97/23/EC Compliant.

50049 3.1.B/EN 10204 3.1.B(2004) compliant. For ABS grades only, Quality Assurance certificate No. 03-MMPQA-182

Pcm = C+(Si30)+(Mn/20)+(Cu/20)+(Ni/60)+(Cr/20)+(Mo/15)+(V/10)+5B

5106285-02

5106285-01

306 314

21.3 22.3

505 512 512 505 497

22.3 21.3

and operations performed by the material manufacturer are in compliance with the applicable specifications We hereby certify that the contents of this report are accurate and correct. All test results

## RAIGHT BILL OF LADING - SHORT FORM

ORIGINAL - NOT NEGOTIABLE

RECEIVED: subject to the classification and tariff in effect on the date of the issue of this Bill of Lading

TELEPHONE 252/356-3700

If this shipment is to be delivered to the consignee without response on the consignor, the consignor shall sign the following statement: The carrier shall not make delivery of this shipment without payment of freight and all other lawful charges.

Subject to Section 7 of Term and Condition. If this shipment is to be delivered to the

BILL OF LADING NO.

Page 1

FROM: NUCOR STEEL - HERTFORD

Freight Term:

109438

1505 River Road AT:

DATE 09/26/2005

Per abaggette (Signature of Consignor)

F.O.B. PREPAID

Cofield, NC

**BOL No. 109438** 

The property described below, in apparent good order, except as noted (contents and condition of contents of packages unknown), marked, consigned, and destined as indicated below, which said carrier (the word carrier being uncerstood throughout this contract as meaning any person or corporation in possession of the property under the contract) agrees to carry its usual place of delivery at said destination. If on its route, otherwise to deliver to another carrier on the route to said destination. It is mutually agreed, as to each carrier of all or any of said property over all or any portion of said route to destination, and as to each party at any time interested in all or any said property, that every service to be performed hereunder shall be subject to all the terms and conditions of the Uniform Domestic Straight Bill of Lading set forth (1) in Uniform Freight Classification in effect on the date hereof, if this is a rail or a rail-water singment, or (2) in the applicable motor carrier classification.

ater simplement, of (2) in the applicable motor carrier classification. Shipper here by certifies that he is familiar with all the terms and conditions of the said bill of lading, set forth in the classification or lawfully filled tariff which governs the transportation of this shipment, and the said terms and and including an expect of the shipper and accepted for himself and his assigns.

SHIP DUFERCO STEEL C/O PLESA ANAHUAC Y CIAS

TO: FOR FURTHERANCE INTO MEXICO

SPECIALIST IN TRANSIT FORWARDING LAREDO TX

LECHERIA. MEX 54940

NCVA - Bovkns - CSXT - Newor - UP - Laredo - TFM

**ROUTE:** STCC 3312253

CARRIER: CSX

SOLD Duferco Steel Inc. TO: 100 Matawan Road

Suite 400

MATAWAN, NJ 07747

CAR OR L/R# : 111495 / Vehicle :ALY 91723

VEHICLE Ticket#: 376640 / Gross Wt:266,248.00 lbs

NO. 2268 miles

			2200 1111165	
Master Plate Pie	eces Customer PO	Product		Order / Line Weight (lbs)
5106284-04	11 1003010027	PLATE - 1" x 96" x 2 Grade: ASTM A36-0	40" 5/ASTM A709 Grade 36-05/ASME SA36-03a	37805 / 3 71,875.58
<u>Heat</u> <u>C</u> 5106284 0.19		<u>Si</u> <u>Cu</u> <u>Ni</u> <u>Cr</u> 0.22 0.24 0.08 0.10	Mo         Sn         AI         V         Nb         N           0.01         0.003         0.009         0.004         0.001         0.0100         0.	<u>Ti</u> <u>B</u> <u>Ca</u> .001 0.0000 0.0013
5106285-01	13 1003010027	PLATE - 1" x 96" x 2 Grade: ASTM A36-0	40" 5/ASTM A709 Grade 36-05/ASME SA36-03a	37805 / 3 84,943.87
5106285-02	4 1003010027	PLATE - 1" x 96" x 2 Grade: ASTM A36-0	40" 5/ASTM A709 Grade 36-05/ASME SA36-03a	37805 / 3 26,136.58
<u>Heat</u> <u>C</u> 5106285 0.18	<u>Mn</u> <u>₽</u> <u>S</u> 0.88 0.014 0.001	<u>Si</u> <u>Cu</u> <u>Ni</u> <u>Cr</u> 0.18 0.26 0.08 0.11	Mo Sn Al V Nb N 0.01 0.005 0.010 0.004 0.001 0.0089 0.	<u>Ti</u> <u>B</u> <u>Ca</u> .001 0.0000 0.0010

Ship To Notes:

PLATES TO BIE SHIPPED IN LIFTS OF SAME SIZE/GRADE OF NO MORE THAN 5 METRIC TONSE-MAIL BOL AND TEST REPORTS

TO m.coakes@duferconj.comSALES ORDER LINES OK TO MIX, DUNNAGE BETWEEN SALES ORDERS

PLATES TO BE SHIPPED IN LIFTS OF SAME SIZE/GRADE OF NO MORE THAN 5 METRIC TONSSALES ORDER LINES OK TO MIX,

DUNNAGE BETWEEN SALES ORDERS

Melted and Manufactured in the USA.

Pieces: 28

Tons: 91.50

lbs: 182,956.03

This is to certify that the above-named articles are properly classified, described, packaged, marked, and labeled, and are in proper condition for transportation according to the applicable regulations of the Department of Transportation.

Shipper's imprints in lieu of stamp, not a part of Bill of Lading approved by the Department of Transportation.

NOTE Where he rate is dependent on value, shippers are required to state postficially in writing he agreed or declared value of the property.

The finer containers used for this shipment conform to the specification set forth in the box maker's certificate thereon, and all other requirements of Rule 41 of the Uniform Freight Classification and Rule 5 of the National Motor Freight Classification.

NUCOR STEEL - HERTFORD P.O. Box 279 Winton, NC 27986

SHIPPER'S SIGNATURE:

CARRIER'S SIGNATURE: