

40460-1
8



CERTIFICADO DE CALIDAD MILL TEST REPORT

LAMINA GALVANIZADA / LAMINA GALVANIZADA PINTADA
GALVANIZED STEEL SHEET / PAINTED GALVANIZED STEEL SHEET

No. FOLIO		
13819		
DIA	MES	AÑO
17	1	2019

ANTIGUA CARRETERA A ROMA KM. 7.7 C.P. 66000 APODACA N.L. MEXICO T+52 (81) 8215 8383 F +52 (81) 8215 8330

CLIENTE / DIRECCION CUSTOMER / ADDRESS	No. PEDIDO ORDER #	CUSTOMER P.O.	NORMA DE CALIDAD ASTM QUALITY STD.
---	-----------------------	---------------	---------------------------------------

PYLSA
PONIENTE 128 672
02300 FRACC. INDUSTRIAL VALLEJO

4700037330
4700037358

ASTM CS TYPE B A653
A653M, A924/A924M
S537

DESCRIPCION DESCRIPTION										PROPIEDADES MECANICAS MECHANICAL PROPERTIES						ANALISIS QUIMICO CHEMICAL ANALYSIS												
No. Rollo Coil No.	Calibre Gauge	Ancho Width		Espesor Thickness		Capa Coating	Acabado Finished	Peso Weight		Largo Length		Dureza Hardness	Elong. %	L. E. Y. S.		R. T. T. S.		Colada Heat	C	MN	P	S	AL	SAE				
		mm	in	mm	in			kg	lb	m	ft			ksi	mpa	ksi	mpa											
A44031G122	26	1219.2	48.000	0.4547	0.0179	Standard	Flor Reg. Pasivado	3,450	7,606	803	2,635	54						190152	0.0640	0.1600	0.0110	0.0120	0.0470	1008				
A47741G12	26	1219.2	48.000	0.4521	0.0178	Standard	Flor Reg. Pasivado	4,225	9,315	985	3,232	52						190152	0.0640	0.1600	0.0110	0.0120	0.0470	1008				
A47741G13	26	1219.2	48.000	0.4648	0.0183	Standard	Flor Reg. Pasivado	4,230	9,326	985	3,232	52						190152	0.0640	0.1600	0.0110	0.0120	0.0470	1008				
A47290G11	16	914.4	36.000	1.5011	0.0591	Standard	Flor Reg. Pasivado	4,110	9,061	382	1,253	60						48882	0.0850	0.3300	0.0180	0.0090	0.0490	1010				
A47306G13	16	914.4	36.000	1.5011	0.0591	Standard	Flor Reg. Pasivado	4,110	9,061	382	1,253	60						188861	0.0940	0.3400	0.0110	0.0130	0.0470	1010				
A46277G21	20	1219.2	48.000	0.9195	0.0362	Standard	Flor Reg. Pasivado	4,900	10,803	568	1,864	60						383129	0.0540	0.1700	0.0090	0.0060	0.0350	1008				
A47269G21	24	914.4	36.000	0.5588	0.0220	Standard	Flor Reg. Pasivado	4,065	8,962	1,034	3,392	60						484840	0.0580	0.1900	0.0130	0.0070	0.0420	1008				
A47269G22	24	914.4	36.000	0.5537	0.0218	Standard	Flor Reg. Pasivado	4,100	9,039	1,043	3,422	57						484840	0.0580	0.1900	0.0130	0.0070	0.0420	1008				
Total :								33,190																				


 Control de Calidad (Quality Control)
 IVAN E. LOPEZ FELIPE