

6600 South Harlem Avenue  
 Argo, IL 60501-1930  
 Phone: (708) 594-1700  
 Fax: (708) 458-0106

**WELDBEND**  
**MATERIAL TEST REPORT**  
**FITTING**

To: PLESA ANAHUAC Y CIA S. SA DE CV.  
 AMERICA DISPATCH INC OF LARDO  
 LAREDO, TX 78045  
 Attn: HEIDI

Order No. 7006

Description	Steel Producer										Tens	Yield	Elong	BHN	
	Heat ID	Cr	Mn	P	S	SI	Cu	Ni	Mo	Ch*					V
4" x 3" XS Reducing Tee	22046	SIDERCA										Heat Treat Normalized			
0.275	.16	.63	.009	.001	.25	.02	.01	.03	.01		< .002	75300	43100	39.00	146
4" x 2" XS Reducing Tee	21189	NKK										Heat Treat Normalized			
0.316	.19	.69	.013	.005	.17	.03	.02	.03	.01			75400	46700	43.00	148
6" x 4" XS Eccentric Reducer	563Z	V & M STAR										Hot Formed			
0.350	.20	.69	.010	.007	.22	.17	.08	.07	.02	.001	.001	73500	50500	34.00	66.00
6" x 3" Std Eccentric Reducer	720Z	US STEEL										Hot Formed			
0.376	.18	1.11	.007	.006	.27	.04	.01	.03	.01	.002	.000	74500	52500	34.00	66.00
16" x 8" Std Reducing Tee	AN879	DALMINE										Heat Treat Stress Relieved			
0.335	.16	.84	.012	.001	.28	.12	.08	.08	.02	.002	.010	73200	48200	44.30	152

All fittings meet the requirements of ASTM A-234 WPB, (and SA-234) and are seamless except as noted. Starting Material Seamless Pipe for elbows, tees and reducers; Plate for caps and welded fittings. ISO 9001:2000 CERTIFIED MANUFACTURER. All fittings meet NACE MR0-175 - Latest Revision. All fittings meet NACE MR0-103 - Latest Revision.



By: *[Signature]*

September 18, 2009

Quality Assurance Department  
 Test Results herein are correct as contained in test records retained by the company.  
 In accordance with EN 10 204 Para 3.1.8  
 In accordance with PED 97/23/EC, 712