

CERTIFIED MATERIAL TEST REPORT

Trinity Fitting Group, Inc.

Hackney * Ladish * Key Bendadis

2525 Stemmons Freeway Dallas, TX 75256 - 888...
 Phone: (214) 589-8177 Fax: (214) 589-8892

BPCS

Order Number: 00000002 (283403-004) DOC #00167610 05/01/12 Date: 01/15/12

Sold to: PLESA ANAHUAC Y CIAS S. A. DE VALLE DE LAS ALAMEDAS NO 66-0 SAN FRANCISCO CHILPAN LAREDO TUXTITLAN EOO DE MEX 54940
 Ship to: PLESA ANAHUAC Y CIAS 001 C/O SPECIALIST IN TRANSIT FWR 1801 MARKLEY - MODERN IND PARK LAREDO TX 78041

Heat Code	Quantity	Description / Specifications	Specification	Heat Code	Quantity
EK04IFS1	35	24 X 16 STD CON	A/SA 234 - 03	EK04IFS1	35
EJ04WSS	50	A106-B 09/S82029	STRESS RELIEVED NORMA	EJ04WSS	50
EL04XDS	50	8 STD CAP	A/SA 234 - 03 WPB	EL04XDS	50
EH04WNS	25	A516-70 154/A4U2046	STRESS RELIEVED	EH04WNS	25
		10 STD CAP	A/SA 234 - 03 WPB		
		154/4106446	STRESS RELIEVED		
		12 STD CAP	A/SA 234 - 03 WPB		
		A516-70 154/A4T1860	STRESS RELIEVED		

Chemical Analysis

Heat Code	Test	C	Mn	P	S	Si	Cu	Ni	Cr	Mo	Al
EK04IFS1	M	.190	1.050	.008	.006	.200	.040	.030	.090	.030	
EJ04WSS	M	.211	1.140	.013	.013	.190	.230	.060	.060	.010	.0130
EL04XDS	M	.190	1.040	.014	.003	.200	.250	.090	.130	.030	
EH04WNS	M	.211	1.160	.009	.006	.200	.180	.060	.070	<.010	.0100

Chemical Analysis (cont.)

Heat Code	N	V	B	Ti	Cb	Sn	W	Pb	Co	CE
EK04IFS1		.001								.391
EJ04WSS	<.010	<.0005	<.0100	<.010	.009	<.002	.002	<.050		.437
EL04XDS		.013		.002						.420
EH04WNS	<.010	<.0005	<.0100	<.010	.007	<.002	.002	<.050		.438

Physical Properties

Heat Code	Tensile KSI	Type	Thickness	Yield KSI	% Elong. (4D)	% RA	Hardness HB
EK04IFS1	76.2	L		42.0	35.0	74.0	137
EJ04WSS	78.5	T		49.9	26.0	54.0	149
EL04XDS	82.3	T		55.2	32.0		156
EH04WNS	83.6	T		51.3	29.0	64.0	141

Charpy Results

Heat Code	Size x 10mm	Type	Temp. (F)	Foot Pounds	Later. Expansion	% Shear
EK04IFS1						
EJ04WSS						
EL04XDS						
EH04WNS						

Test: M=Mill Product
 Type: L=Longitudinal T=Transverse

We certify that the material herein described has been manufactured, heat treated, sampled, tested, and inspected in accordance with the above standards and specifications and satisfies those requirements. We certify these flanges and fittings capable of passing a hydrostatic test compatible with their rating. The above figures are correct as contained in the records of the Company. This information has been electronically transmitted to our customer.
 /S/ Glinda LaFleur