



VALVULAS WORCESTER DE MEXICO, S.A. DE C.V.

RHINO VALVES WORLDWIDE



CERTIFICADO DE CALIDAD/QUALITY CERTIFICATE

EN 10 204 3.1 B


Factura / Invoice:	Cantidad / Quantity:	Certificado / Certificate:	Fecha / Date:
98830	200.00	FE98830/67	10/Feb/04
Descripción / Description:			
TCA. UNION (1/2") NPT L-3000 #			
Cliente / Customer:			
7 TUBOS CONEXIONES Y TANQUES. S. A. DE C. V.			


Válvulas Worcester de México, S.A. de C.V., certifica que el material indicado cumple con nuestras especificaciones como se describe en nuestras catálogos, hojas de especificación, dibujos y en otra literatura. Los productos, partes, materiales indicados aquí han sido comprados, fabricados, inspeccionados, probados de acuerdo con estas especificaciones, a nuestro sistema de calidad ISO 9001 y ASME/ANSI B16.34-1998 inciso (7..ASME / ANSI B16 11-1996, MSS SP-83-1995.

Válvulas Worcester de México, S.A. de C.V., hereby certifies that the material supplied is in accordance with our specifications as describe in our catalog, specification sheets, drawings, and other literature. The products, parts and materials identified herein have been purchased, manufactured, inspected and tested in accordance with these specifications, our ISO 9001 quality assurance program and ASME/ANSI B16.34-1998 part (7.. ASME / ANSI B16 11-1996, MSSP SP-83-1995.

ORIGINAL




Elaboro / Elaborated by: 
 Jose Luis Perez C.
 Metrologista

Aprobo / Aproved by: 
 Ing. Saturnino Padilla Becerra.
 Gerente de Aseguramiento de Calidad
 Quality Ass. Manager

Maiz No. 263, Colonia Valle del Sur, Delegación Iztapalapa, México D.F. C.P. 09819

Teléfonos: 56-70-51-55 (8 líneas) 56-70-86-24 55-82-91-03 5582-30
 Fax: 56-70-87-41 56-70-35-13 e-mail: calidadw@worcester.com.mx



VALVULAS WORCESTER DE MEXICO, S.A. DE C.V.
RHINO VALVES WORLDWIDE



CERTIFICADO DE CALIDAD / QUALITY CERTIFICATE

CERTIFICADO / CERTIFICATE:

EE:9883067

MATERIAL	CDMA	NO. COLADA	
ASTM A105		NO. HEAT	
	X		
	X		
	X		

CDMA	0.190	1.050	0.200	0.008	0.010	0.200	0.010	0.100	0.130	0.003	X	0.012	X	X	X	X	RESISTENCIA A LA TENSION	TENSILE STRENGTH	LIMITE DE CEDENCIA	YIELD STRENGTH	% ELONGACION	% ELONGATION	REDUCCION DE AREA	REDUCTION AREA	DUREZA	HARDNESS
-	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	524 N/mm ²		342 N/mm ²		28.600		64.200		160 HB	X
-	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X					X				X	X
-	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X					X				X	X
-	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X					X				X	X
-	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X					X				X	X
-	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X					X				X	X
-	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X	X					X				X	X

ORIGINAL